

## **ANTIQUE COLONIAL**



### **The perfect blend of old and new in a Clay Brick**

Colourful and popular bricks, Shaw Brick's Colonial Collection is the perfect blend of old and new in a contemporary clay brick. The random textures and colouring of each brick create unique patterns with each installation.

### **Inspired by the great colonial brick building traditions**

Inspired by the great building traditions of New England and Atlantic Canada, the Colonial Collection evokes the time-honoured colours and textures of classic colonial masonry with colour variations, dimpling and distressed textures in the brick face.

The Colonial Collection of Clay Bricks is available in: Cambridge, Antique, Lowell Historic and, as special orders: Brunswick, Heritage, Old Scotia, Antique White and Harvard. Antique is also available as a slender brick, as a special order.

Drop into a [Shaw Retail Centre](#) or one of our [independent dealers](#) to see samples of these bricks for sale and to learn more about any product in the Shaw Masonry Collection.

## **SPECIFICATIONS**



20 Clay Brick Way  
 Lantz, NS B2S 3G4  
 (902) 883-2201  
 salesinfo@shawbrick.ca

## Brick Measurement Chart

Sizes	Metric	Imperial	Approximate Weight	Pc/Pallet	Coverage
Modular	57x90x190mm	2 ¼" x 3 ½" x 7 5/8"	4lbs	500	7 pcs/sqft
Saxon	90x90x190mm	3 ½" x 3 ½" x 7 5/8"	6lbs	305	4.9 pcs/sqft
Max 57	57x90x255mm	2 ¼" x 3 ½" x 10 1/8"	5lbs	400	5.2 pcs/sqft
Ontario	60x102x213mm	2 3/8" x 4" x 8 3/8"	5lbs	395	6 pcs/sqft
CSR	70x90x230	2 3/4" x 3 1/2" x 9 1/16"	6lbs	380	4.9 pcs/sqft
MAX	79x90x290	3 1/8" x 3 1/2" x 10 1/8"	7lbs	276	3.9 pcs/sqft
Slender	12.7x90x190mm	1/2" x 3 1/2" x 7 5/8"	28lbs/box	34pcs/box	7 pcs/ sqft

**Note:** Not all bricks are available in all sizes as indicated. Please contact your Shaw Brick Sales Representative or email salesinfo@shawbrick.ca for minimum special order quantities and production lead times.

## Clay Brick Product Specifications

CSA STANDARD VS. SHAW – TYPICAL TEST REPORT				
Property	CSA Standard A82-06	SHAW BRICK		
		Red	Brown	Buff
Minimum Compressive Strength Gross Area MPa (P.S.I.)	20.68 (3,000)	80 – 100 (11,000 – 14,000)	70 – 90 (10,000 – 13,000)	65-85 (9,500 – 12,000)
Maximum Water Absorption 24 hr. %	8.0	1 – 3	2 – 4	6 – 8
Maximum Saturation Coefficient	0.78	0.65 – 0.78	0.50 – 0.70	0.70 – 0.78
Maximum Initial Rate of Absorption	30g/min/ 20,000mm <sup>2</sup>	1 – 5	5 – 20	10 – 20
Freeze Thaw % After 50 Cycles	Less than 0.5% loss in dry mass	Meets Requirements		

To view more photos and for more information on this product, visit: [shawbrick.ca/products/colonial-antique/](http://shawbrick.ca/products/colonial-antique/)