

ANTIQUE WHITE COLONIAL



The perfect blend of old and new in a Clay Brick

Colourful and popular bricks, Shaw Brick's Colonial Collection is the perfect blend of old and new in a contemporary clay brick. The random textures and colouring of each brick create unique patterns with each installation.

Inspired by the great colonial brick building traditions

Inspired by the great building traditions of New England and Atlantic Canada, the Colonial Collection evokes the time-honoured colours and textures of classic colonial masonry with colour variations, dimpling and distressed textures in the brick face.

The Colonial Collection of Clay Bricks is available in: Cambridge, Antique, Lowell Historic and, as special orders: Brunswick, Heritage, Old Scotia, Antique White and Harvard. Antique is also available as a slender brick, as a special order.

Drop into a [Shaw Retail Centre](#) or one of our [independent dealers](#) to see samples of these bricks for sale and to learn more about any product in the Shaw Masonry Collection.

SPECIFICATIONS



20 Clay Brick Way
 Lantz, NS B2S 3G4
 (902) 883-2201
 salesinfo@shawbrick.ca

Brick Measurement Chart

| Sizes | Metric | Imperial | Approximate Weight | Pc/Pallet | Coverage |
|---------|---------------|---------------------------|--------------------|-----------|--------------|
| Modular | 57x90x190mm | 2 ¼" x 3 ½" x 7 5/8" | 4lbs | 500 | 7 pcs/sqft |
| Saxon | 90x90x190mm | 3 ½" x 3 ½" x 7 5/8" | 6lbs | 305 | 4.9 pcs/sqft |
| Max 57 | 57x90x255mm | 2 ¼" x 3 ½" x 10 1/8" | 5lbs | 400 | 5.2 pcs/sqft |
| Ontario | 60x102x213mm | 2 3/8" x 4" x 8 3/8" | 5lbs | 395 | 6 pcs/sqft |
| CSR | 70x90x230 | 2 3/4" x 3 1/2" x 9 1/16" | 6lbs | 380 | 4.9 pcs/sqft |
| MAX | 79x90x290 | 3 1/8" x 3 1/2" x 10 1/8" | 7lbs | 276 | 3.9 pcs/sqft |
| Slender | 12.7x90x190mm | 1/2" x 3 1/2" x 7 5/8" | 28lbs/box | 34pcs/box | 7 pcs/ sqft |

Note: Not all bricks are available in all sizes as indicated. Please contact your Shaw Brick Sales Representative or email salesinfo@shawbrick.ca for minimum special order quantities and production lead times.

Clay Brick Product Specifications

| CSA STANDARD VS. SHAW – TYPICAL TEST REPORT | | | | |
|--|-----------------------------------|-------------------------------|------------------------------|---------------------------|
| Property | CSA Standard A82-06 | SHAW BRICK | | |
| | | Red | Brown | Buff |
| Minimum Compressive Strength Gross Area MPa (P.S.I.) | 20.68 (3,000) | 80 – 100 (11,000 – 14,000) | 70 – 90 (10,000 – 13,000) | 65-85 (9,500 – 12,000) |
| Maximum Water Absorption 24 hr. % | 8.0 | 1 – 3 | 2 – 4 | 6 – 8 |
| Maximum Saturation Coefficient | 0.78 | 0.65 – 0.78 | 0.50 – 0.70 | 0.70 – 0.78 |
| Maximum Initial Rate of Absorption | 30g/min/ 20,000mm ² | 1 – 5 | 5 – 20 | 10 – 20 |
| Freeze Thaw % After 50 Cycles | Less than 0.5% loss in dry mass | Meets Requirements | | |

To view more photos and for more information on this product, visit: shawbrick.ca/products/colonial-antique-white/