

BRUNSWICK COLONIAL



The perfect blend of old and new in a Clay Brick

Colourful and popular bricks, Shaw Brick's Colonial Collection is the perfect blend of old and new in a contemporary clay brick. The random textures and colouring of each brick create unique patterns with each installation.

Inspired by the great colonial brick building traditions

Inspired by the great building traditions of New England and Atlantic Canada, the Colonial Collection evokes the time-honoured colours and textures of classic colonial masonry with colour variations, dimpling and distressed textures in the brick face.

The Colonial Collection of Clay Bricks is available in: Cambridge, Antique, Lowell Historic and, as special orders: Brunswick, Heritage, Old Scotia, Antique White and Harvard. Antique is also available as a slender brick, as a special order.

Drop into a [Shaw Retail Centre](#) or one of our [independent dealers](#) to see samples of these bricks for sale and to learn more about any product in the Shaw Masonry Collection.

SPECIFICATIONS



20 Clay Brick Way
 Lantz, NS B2S 3G4
 (902) 883-2201
 salesinfo@shawbrick.ca

Brick Measurement Chart

Sizes	Metric	Imperial	Approximate Weight	Pc/Pallet	Coverage
Modular	57x90x190mm	2 ¼" x 3 ½" x 7 5/8"	4lbs	500	7 pcs/sqft
Saxon	90x90x190mm	3 ½" x 3 ½" x 7 5/8"	6lbs	305	4.9 pcs/sqft
Max 57	57x90x255mm	2 ¼" x 3 ½" x 10 1/8"	5lbs	400	5.2 pcs/sqft
Ontario	60x102x213mm	2 3/8" x 4" x 8 3/8"	5lbs	395	6 pcs/sqft
CSR	70x90x230	2 3/4" x 3 1/2" x 9 1/16"	6lbs	380	4.9 pcs/sqft
MAX	79x90x290	3 1/8" x 3 1/2" x 10 1/8"	7lbs	276	3.9 pcs/sqft
Slender	12.7x90x190mm	1/2" x 3 1/2" x 7 5/8"	28lbs/box	34pcs/box	7 pcs/ sqft

Note: Not all bricks are available in all sizes as indicated. Please contact your Shaw Brick Sales Representative or email salesinfo@shawbrick.ca for minimum special order quantities and production lead times.

Clay Brick Product Specifications

CSA STANDARD VS. SHAW – TYPICAL TEST REPORT				
Property	CSA Standard A82-06	SHAW BRICK		
		Red	Brown	Buff
Minimum Compressive Strength Gross Area MPa (P.S.I.)	20.68 (3,000)	80 – 100 (11,000 – 14,000)	70 – 90 (10,000 – 13,000)	65-85 (9,500 – 12,000)
Maximum Water Absorption 24 hr. %	8.0	1 – 3	2 – 4	6 – 8
Maximum Saturation Coefficient	0.78	0.65 – 0.78	0.50 – 0.70	0.70 – 0.78
Maximum Initial Rate of Absorption	30g/min/ 20,000mm ²	1 – 5	5 – 20	10 – 20
Freeze Thaw % After 50 Cycles	Less than 0.5% loss in dry mass	Meets Requirements		

To view more photos and for more information on this product, visit: shawbrick.ca/products/colonial-brunswick/